



IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of:

Michihisa TASAKA et al.

Serial No.: 09/384,380

Group Art Unit: 1713

Filed: August 27, 1999

Examiner: Rip A. Lee

For: FIRE-RETARDANT RESIN COMPOSITION AND MOLDED PART USING THE
SAME

DECLARATION UNDER 37 C.F.R. § 1.132

Honorable Commissioner of Patents
and Trademarks
Washington, D.C. 20231

Sir:

I, Kazuhiko KOBAYASHI, declare and state that:

1. I am a Japanese citizen residing at 3-26-7, Sugita,
Isogo-ku, Yokohama-shi, Kanagawa-ken, Japan.

I was graduated from Science & Engineering Section, CHUO
University in March 1982.

I have been employed by RIKEN VINYL INDUSTRY CO., LTD.
(whose name is changed to RIKEN TECHNOS CORPORATION as of October
1, 2001) since April 1982. I engaged in research and development
of insulating-materials for electric wires at Compound Technical
Department of the said company since April 1985. Further, I have
been engaged in research and development of insulating-materials
for electric wires in Polymer Application R&D Department at
Material Research Center of the said company since April 1998.

I am intimately familiar with the contents of United States

RECEIVED
JUL 24 2002
TC 1700

Patent Application Serial No. 09/384,380, filed on August 27, 1999, its prosecution before the United States Patent & Trademark Office, and the references cited therein.

2. I have studied the content of the cited Tasaka et al.'s U.S. Patent No. 5,929,165, Aida et al.'s U.S. Patent No. 5,221,781, and Nosu et al.'s U.S. Patent No. 6,218,454.

3. To show the superiority of the present invention, the following tests were conducted, by me or under my supervision:

Test

A resin composition, Comparative example A, was prepared in the same manner as in Example 1 in the present specification, except that the ethylene/ α -olefin copolymer was changed to another ethylene/ α -olefin copolymer. That is, Excellen VL 200 (trade name, manufactured by Sumitomo Chemical Co., Ltd.), which was a very low-density straight-chain polyethylene synthesized in the presence of a multi site catalyst (MFR, 2.0 g/10 min; Density, 0.90 g/cm³), was used in Comparative example A, in place of the ethylene/ α -olefin copolymer (c-1) in Example 1 synthesized in the presence of a single site catalyst.

From the thus-obtained resin composition, a 1-mm sheet, corresponding to Comparative example A, was obtained in the same manner as described in the EXAMPLES section (lines 11 to 13 on page 55) of the present specification.

Also, from the thus-obtained resin composition, an insulated wire, corresponding to Comparative example A, was

obtained in the same manner as described in the EXAMPLES section (from line 14, page 55, to line 10, page 56) of the present specification.

Furthermore, from the thus-obtained resin composition, a power source plug, molded by injection-molding, corresponding to Comparative example A, was obtained in the same manner as described in the EXAMPLES section (lines 11 to 18, page 56) of the present specification.

As to the thus-obtained sheet, the tensile properties (extension (elongation) (%) and tensile strength (MPa)) and the heat deformation property were evaluated, in the same manner as described in the EXAMPLES section (lines 19 to 24, page 56) of the present specification. The results are also shown in Table I below.

Further, regarding the covering layer of the thus-obtained insulated wire, the tensile properties, abrasion resistance, the horizontal flame test, the 60°-inclined flame test, the heat deformation rate test, the whitening test (whether a whitening phenomenon was observed when bent), the extrudability test, and the flexibility test were carried out, in the same manner as described in the EXAMPLES section (from line 4, page 57, to line 3, page 61) of the present specification. The results are also shown in Table I.

Additionally, for the molded plug, the horizontal flame test and the 60°-inclined flame test were carried out, in the same

manner as described in the EXAMPLES section (from line 22, page 58, to line 8, page 59) of the present specification. Further, for the molded plug, the whitening test (whether a whitening phenomenon was observed when bent) was carried out, and the moldability was observed, which was judged from observing the outer appearance of the molded product. The results are also shown in Table I.

Further, for reference, the resin composition of Example 1 was used to prepare a power source plug in the same manner as mentioned above, and the plug was tested as well. The results are also shown in Table I. In addition, as the conditions and results for the sheet and the insulated wire of Example 1, as shown in Table 1 in the specification of the present application, are again shown in Table I below. Example 1 employed an ethylene/ α -olefin copolymer synthesized in the presence of a single site catalyst.

Table I

		Comparative example A	Example 1
a	SEPS	100	100
b	Paraffin oil	40	40
c-1	Ethylene/ α -olefin copolymer (ethylene/1-octene copolymer synthesized using single site catalyst) (Density, 0.870)	none	133
	Ethylene/ α -olefin copolymer (very low-density straight-chain polyethylene synthesized using multi site catalyst) (Density, 0.90)	133	none
d-1	Block polypropylene	33	33
e	Organic peroxide	0.66	0.66
f	Crosslinking aid	2	2
	Maleic acid-modified LLDPE	27	27
B-1	Kisma 5LH	500	500
	Antioxidant	3	3
	Lubricant	6	6
Properties of the sheet	Extension (%)	210	200
	Tensile strength (MPa)	15	19
	Heat deformation at 121 °C (%)	13	13
Characteristics of the electric wire	Extension (%)	220	220
	Tensile strength (MPa)	16	20
	Horizontal flame test	10/10	10/10
	60°-inclined flame test	10/10	10/10
	Abrasion resistance	○	○
	Whitening	x	○
	Heat deformation (%)	19	21
	Extrudability	x	○
	Flexibility	x	○
	Horizontal flame test	10/10	10/10
Characteristics of the injection-molded plug	60°-inclined flame test	10/10	10/10
	Whitening	x	○
	Moldability (Outer appearance)	○	○

Whitening

Moldability, when molding was possible with a normal load and resulted in molded plugs having good outer appearance (which was good and rated "O"); on the other hand when molding was difficult or impossible so that poor outer appearance was observed on the molded plug (which was poor and rated "X");

In the results of the horizontal flame test, the number of samples that passed the test (per 10 trials) were shown; and in the results of the 60°-inclined flame test, number of samples that passed the test (per 10 trials) were shown.

As is apparent from the results shown in Table I, each of the sheet, the insulated wire, and the molded plug prepared employing the ethylene/ α -olefin copolymer synthesized in the presence of a single site catalyst (Example 1), exhibited unexpectedly superior results in some of the evaluation items, such as tensile strength, whitening, extrudability, and flexibility, compared with those prepared employing the ethylene/ α -olefin copolymer synthesized in the presence of a multi-site catalyst (Comparative example A).

Specifically, the wire prepared employing the resin composition of Comparative example A was conspicuously inferior in whitening, extrudability, and flexibility (rated "X") compared with one prepared employing the resin composition of Example 1 (rated "O").

Additionally, the molded plug prepared employing the resin composition of Comparative example A was conspicuously inferior

in whitening (rated "X") compared with one prepared employing the resin composition of Example 1 according to the present invention (rated "O").

Accordingly, it should be apparent that the fire-retardant resin composition and the molded part according to the present invention, each of which employs an ethylene/ α -olefin copolymer synthesized using a single site catalyst, are excellent in each item of the properties including not only mechanical characteristics, such as tensile strength, and heat resistance but also extrudability, flexibility, moldability and whitening.

In my Declaration of December 26, 2001, I declared I was one of the inventors of the subject matter of United States Patent Application Serial No. 09/384,380, but it was a clerical error.

The data already of record in the specification and the supplemental data submitted herewith demonstrate unexpectedly superior results of the claimed fire-retardant resin composition, molded part, and method for processing fire-retardant resin composition over those of the cited prior art.

4. I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the

United States Code and that such willful false statements may
jeopardize the validity of the application or any patent issuing
thereon.

Date: July 19, 2002

K Kobayashi
Kazuhiko KOBAYASHI